

MAXTER GLOVE MANUFACTURING SDN BHD GLOVE SPECIFICATION

1. Product : (5.0g) Smooth Surface Powdered Latex Examination Gloves
2. Material : Natural Rubber Latex
3. Type : Non Sterile
4. Glove Design & Feature : Ambidextrous, Smooth Surface
5. Cuff : Beaded
6. Usage : For Single Use Only
7. Colour : Beige
8. Packaging : 100 ± 2 pcs/inner, 10 or 20 inners/carton

Size	Glove Weight (g)	Palm Width (mm)		Length (mm)	
		ASTM D3578	MAXTER	ASTM D3578	MAXTER
XS	4.3 ± 0.2	70 ± 10	70 – 79	Min. 220	Min. 240
S	4.6 ± 0.2	80 ± 10	80 – 89	Min. 220	Min. 240
M	5.0 ± 0.2	95 ± 10	90 – 99	Min. 230	Min. 240
L	5.4 ± 0.2	110 ± 10	100 – 109	Min. 230	Min. 240
XL	5.9 ± 0.2	120 ± 10	110 – 119	Min. 230	Min. 240

Location of Thickness Measurement	Single Wall (mm)	
	ASTM D3578	MAXTER
Finger	Min 0.08	Min 0.08
Palm	Min 0.08	Min 0.08


	Before Aging		After Aging	
	ASTM D3578	MAXTER	ASTM D3578	MAXTER
Tensile Strength (MPa)	Min. 18	Min. 18	Min. 14	Min. 14
Elongation (%)	Min. 650	Min. 650	Min. 500	Min. 500

12. Protein Content : Max. 200 µg/dm²
13. Powder Level : Max. 10 mg/ dm²
14. Compliance Standards : ASTM D3578, EN 455 Part 1 & 3.

Inspection Criteria (Sampling & Inspection ISO 2859)	Inspection Level		ΔQL
	ASTM D3578	MAXTER	
Watertight Test	G1	G1	1.5
Major Defects	G1	G1	2.5
Minor Defects	G1	G1	4.0
Dimensions	S2	S2	4.0
Physical Properties	S2	S2	4.0

16. Quality Assurance : ISO 9001 certified by SGS (UK) and SIRIM (Malaysia)
ISO 13485 certified by SGS (UK)

Prepared by : 
Yap Peak Geoh
QA & RA Manager

Approved by : 
Dato' Seri Stanley Thai
Group MD

